

Mambo

Secondary Backing Rugtype • Envers Rücken • Sottofondo	PF / SB	EN 1307-2004 Classification Classificatie • Classification Klassifizierung • Classificazione	Class 31 Commercial Moderate
Manufacturing process Fabricagemethode • Technique de fabrication Herstellungsart • Tecnica di fabbricazione	tufted, 1/10" cut pile	ISO 140/8 1997 Impact sound insulation Contactgeluidsisolatie • Isolation aux bruits d'impact Trittschallverbesserungsmaß • Miglioramento acustico	PF ± 28 dB
Pile composition Poolsamenstelling • Nature du velours Polmaterial • Composizione felpa	PA	ISO 354 Sound absorption α_s Geluidsdempingsvermogen α_s • Absorption phonique α_s Schallabsorptionsgrad α_s • Grado d'assorbimento acustico α_s	PF ± 0,53 (1000 Hz)
Primary backing Tuftdoek • Premier dossier Trägermaterial • Tela di supporto	woven	ISO 11654 Sound absorption α_w Geluidsdempingsvermogen α_w • Absorption phonique α_w Schallabsorptionsgrad α_w • Grado d'assorbimento acustico α_w	PF ± 0,25
Width Breedte • Largeur Breite • Altezza	± 400 cm	DIN 52612 Thermal retention Warmtedoorlaatweerstand • Résistivité thermique Wärmedurchlaßwiderstand • Resistenza termica	SB ± 0,07 m²/kW
Effective pile height Nuttige poolhoogte • Hauteur de velours utile Tatsächliche Florhöhe • Spessore felpa utile	± 4,0 mm	TOG rating	SB ± 0,7
Total height Totale dikte • Hauteur totale Gesamthöhe • Spessore totale	PF ± 7 mm SB ± 6 mm	ISO 105 B02 2000 Lightfastness Lichtechtheid • Solidité à la lumière Lichtechtheit • Solidità colori alla luce	≥ 5-6
Number of knots/sqm Aantal noppen/m ² • Nombre de points/m ² Noppenzahl/m ² • Numero di punti/mq	± 204.880	ISO 105 E01 2002 Waterfastness change in colour Waterechtheid verkleuring • Solidité à l'eau changement couleur Wasserechtheit Änderung der Farbe • Solidità colori all'acqua cambio colore	≥ 4
Pile weight/sqm Poolinzetgewicht/m ² • Poids mis en oeuvre/m ² Poleinsatzgewicht/m ² • Peso felpa/mq	± 450 gr	ISO 105 E01 2002 Waterfastness staining Waterechtheid uitbloeding • Solidité à l'eau dégorgeement Wasserechtheit anbluten • Solidità colori all'acqua sfumatura colore	≥ 3-4
Total weight/m² Totaal gewicht/m ² • Poids total/m ² Gesamtwicht/m ² • Peso totale/m ²	PF ± 1.650 gr SB ± 1.520 gr	ISO 105 X12 2001 Rubbingfastness dry Wrijfchtheid droog • Solidité au frottement sec Reibungechtheit trocken • Solidità colori allo sfregamento a secco	≥ 4-5
EN 13501-1 Fire behaviour Brandgedrag • Comportement au feu Brennverhalten • Reazione al fuoco	C_{fl}-s1	ISO 105 X12 2001 Rubbingfastness wet Wrijfchtheid nat • Solidité au frottement humide Reibungechtheit nass • Solidità colori allo sfregamento umido	≥ 4-5

(±) These details are approximate. Complete specification details and associated certificates together with tolerances applying to the above can be provided upon request. We reserve the right to improve technical specifications without prior notice. Due to method of manufacture perfect pattern and/or colour matching cannot be guaranteed. In cut-pile carpeting, in rare cases, shading pile reversal may occur without affecting its fitness for use. Shading/pile reversal can not be considered as a manufacturing or a material defect and will not affect the durability of the carpet. For other languages see: www.lano.com

PF

10
EN 14041
DOP 1038-113014
NB 0493

GUT
20865

364DCFF6
www.pro-dis.info

MOQUETTES TOUFFETÉES
ET TISSÉES EN LES

QB UPEC
2s 2 1 0
04/156
<http://evaluation.cstb.fr>

100%
PA

ISO 9001
BQA_QMS019_C_199460

SB

10
EN 14041
DOP 1038-113496
NB 2401

GUT
23686

DC64DBAD
www.pro-dis.info

MOQUETTES TOUFFETÉES
ET TISSÉES EN LES

QB UPEC
2s 2 1 0
04/156
<http://evaluation.cstb.fr>

100%
PA

ISO 9001
BQA_QMS019_C_199460

The Green signature
of Lano Carpets

REACH
The new EU chemicals legislation

EMISSIONS DANS L'AIR INTÉRIEUR
A+